

Treatment report

The photograph was surface cleaned with light moisture to remove surface grime. Losses and fragments were filled and re-attached with Whatman CF-11 cellulose powder and Klucel-G. The reverse of the original backing was alkalized non-aqueously with Bookkeeper spray. Image losses were toned with Winsor & Newton watercolor. The photograph was digitally scanned with enhancement to the digital file. The cross corner frame back was extended to accommodate additional supports. The photograph was backed with 100% rag matboard, UV filtered glass and spacers. The supports were backed with MarvelSeal™ and re-housed in the original frame.