

## Treatment

The prints from Stacks 1 and 2 were treated aqueously in cold water and Kodak Photo-Flo to separate. Areas of emulsion loss and superficial tears were consolidated using a 2% per 20 mL soln. of photographic grade gelatin. The prints were flattened. L-sleeves of 4mil. polyester were provided for each print.